



Deco Cryl

High-Coverage Acrylic Paint

Water-based coating for exterior masonry surfaces. It provides a smooth, matt, velvety finish of excellent aesthetic quality.

APPLICATION TOOLS



PACKAGING



CHARACTERISTICS

- ✓ High whiteness
- ✓ Excellent hiding power
- ✓ Weather resistant
- ✓ High spreading rate
- ✓ Easy to apply
- ✓ Excellent flexibility

SURFACES / USES

- ✓ Concrete
- ✓ Plasterboard
- ✓ Plaster
- ✓ Brick
- ✓ Wood

TECHNICAL DATA

Appearance	Viscous liquid
Shade	White
Coverage	9-11 m ² /L
Density	1,55 ± 0,02 g/cm ³
Thinning	5-10% with Water
pH	8-9
Binder	ACRYLIC
Touch dry	30min
Ideal application and drying temperature	15 - 25°C
Viscosity	7500-8.500 mPa·s at 23°C
Through dry	4hr
Solids by weight	61 %
Recoating time	3hr

(*) Exact drying times depend on the ambient temperature and relative humidity during application and drying.



Surface Preparation

- Apply on dry, clean surfaces, free from materials that may prevent adhesion.
- Successful application depends on proper substrate preparation and correct application of the material.
- Clean the surface from foreign particles, dust and residues.
- Prime the surface with two coats, using either plastic primer or solvent-thinnable Desmo Seal primer.



Application

- Once the primer begins to dry, apply Deco Cryl acrylic paint.
- To adjust viscosity, it may be diluted with 5-10% water.
- The second coat should be applied after the first coat has dried.



Restrictions

Do not apply at temperatures below 5°C or above 40°C.
Do not apply when the relative humidity exceeds 80%.
Allow damp surfaces to dry thoroughly before application.
Protect the freshly painted surface from cold and moisture for at least 24 hours.



Tools Cleaning

During application, keep tools "wet" inside the container or paint tray. Drain the paint thoroughly from the tools back into the tin and clean them first with white spirit and then with soap and water.



Storage

Store for up to one year in the original sealed container at temperatures between 5°C and 40°C.



Precautions

CONTAINS: reaction mass of 5-chloro-2-methyl-4-isothiazolin-3-one [EC No. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC No. 220-239-6] (3:1). May produce an allergic reaction.



VOC Category

Product of Category A/c (WB) "Exterior walls of mineral substrate" of European Directive 2004/42 / EC. Category VOC limit value: 40gr/ltr. The maximum VOC content of the ready-to-use product is 39gr/ltr.