



Total Fix On The Top

Fast-drying industrial synthetic enamel paint

Fast-drying alkyd-based anti-corrosion synthetic enamel paint for metal surfaces.

It creates a hard and glossy surface, offering an attractive finish and long-lasting gloss.

APPLICATION TOOLS



PACKAGING



CHARACTERISTICS

- ✓ Fast drying
- ✓ High gloss and hardness
- ✓ Excellent opacity

SURFACES / USES

- ✓ Metal

TECHNICAL DATA

Appearance	Viscous liquid
Shade	White, black, grey, terracotta
Coverage	10-12m ² /lt per coat
Density	1.05 ± 0.02 gr/cm ³
Thinning	5% with Spray Gun Thinner
Touch dry	15-20min
Viscosity	2000-2500 mPa·s at 23°C
Recoating time	2-3hr

(*) Exact drying times depend on the ambient temperature and relative humidity during application and drying.



Surface Preparation

- Apply on dry, clean surfaces, free from materials that may prevent adhesion.
- Successful application depends on proper substrate preparation and correct application of the material.
- Remove any silicone or oils from the metal surface using thinner.
- Prime the surface with one or two coats of Total Fix Rapid metal primer.



Application

- Once the primer has dried, apply Total Fix On The Top enamel paint in two coats.
- The second coat should be applied after the first coat has dried.
- To adjust viscosity, it may be diluted with 5% spray-gun thinner or nitro thinner.



Tools Cleaning

During application, keep tools "wet" inside the container or paint tray. Drain the paint thoroughly from the tools back into the tin and clean them with spray-gun thinner.



VOC Category

Product of Category A / i (SB) * "One-pack performance coatings" of European Directive 2004/42 / EC. Category VOC limit value: 500gr/lt. The maximum VOC content of the ready-to-use product is 499gr/lt.



Restrictions

Do not apply at temperatures below 5°C or above 35°C. Do not apply when the relative humidity exceeds 80%. Allow damp surfaces to dry thoroughly before application.



Storage

Store for up to one year in the original sealed container at temperatures between 5°C and 40°C.